

► DPF 4300 Multi-Purpose Film

Intermediate Calendered White Multi-Purpose Removable Film

DPF 4300 is a 86 microns opaque matte white calendered film with removable adhesive. The film is a multi-purpose clean removable film for an easy on & easy off application. It offers flexibility as well as high opacity for covering previous graphics up to three layers applied within six months or less. DPF 4300 also provides good resistance to scuffing, tearing, and abrasion to help protect your graphics. The adhesive allows clean removability on a variety of substrates such as painted metal and plastics for one year. DPF 4300 is fire certified under ASTM E-84 and EN 13501-1:2007+A1:2009 of Euro Class C, s1, d0 and rated for outdoor durability up to 4 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Ultra clean removing for up to one year
- Multi-purpose applications; painted walls*, windows, short-term vehicle advertising, decals
- Matte white flexible opaque film offers high opacity for covering previous graphics and dark substrates*
- Compatible with Series 3200, Series 3210, Series 3220 and Series 3420 overlaminates
- Print Compatibility: Solvent, Eco-Solvent, UV and Latex

* Due to changes in the paint industry, best practice is to conduct the vinyl-wall compatibility test with wall paint.

* Previous graphics must be less than six months old and only up to three layers.

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE
SURFACE FINISH	Gloss Meter 60° Reflection	9 Gloss Units
THICKNESS	Micrometer, Federal Bench Type	86 microns
TENSILE STRENGTH	Tensile Tester with 51 mm jaw separation; crosshead speed of 5.1 mm/s, web direction	2.59 kg/cm
ELONGATION	Instron Tensile Tester as above	250%
SHELF LIFE (IN BOX)	Ideal Storage Temperature 21°C and 50% relative humidity	2 years from factory shipment
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	10°C to 32°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-29°C to 80°C
DIMENSIONAL STABILITY	Shrinkage After 70°C, 48 hours aging	< 508 mm
PEEL ADHESION	PSTC-1, 15 min, 21°C	0.18 kg/cm
LINER RELEASE	TLMI Release at 90°, 760 cm/min	12.8 g/cm

Standard Terms & Conditions Apply

TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

October 2019

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA
EUROPE:  Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands

 +1 714 985 6300  800 329 2756
 +31 70 354 4311  +31 70 355 7721

arlon.com