

## ► DPF 4500GLX / MLX Vinyl Film

### Intermediate Polymeric Digital Print Pressure-Sensitive Vinyl Film with X-Scape Technology®

DPF 4500GLX / MLX is constructed of a 75 microns white polymeric film offered in gloss or matte and coated with tinted, bubble releasing, permanent pressure-sensitive and solvent-based adhesive. The LX (Low Profile) X-Scape System allows installers to achieve speedy installation while maintaining high enough tack to ensure long-term bond. The polymeric facestock allows for vibrant prints combined with ease of application for short and medium-term graphics. DPF 4500GLX / MLX is rated for outdoor durability up to 5 years (unprinted). Printed durability is dependent on the ink system used.

### APPLICATIONS & FEATURES

- Digital printing with a wide variety of direct print systems
- Short to medium-term signage, POP displays, flat surfaces, kiosks and tradeshow\*

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	80 to 90 Gloss Units (Gloss) 10 to 15 Gloss Units (Matte)
<b>THICKNESS</b>	Micrometer, Federal Bench Type	75 microns
<b>TENSILE STRENGTH</b>	Tensile Tester 51mm jaw separation; crosshead speed of 5.1 mm/s	2.3 kg/cm
<b>ELONGATION</b>	Instron Tensile Tester as above	≥ 170%
<b>SHELF LIFE (IN BOX)</b>	Ideal Storage Temperature 21°C and 50% relative humidity	1 year from factory shipment
<b>APPLICATION TEMPERATURE RANGE</b>	On clean, dry substrate	10°C to 32°C
<b>SERVICE TEMPERATURE RANGE</b>	On clean, dry substrate	-29°C to 65°C
<b>DIMENSIONAL STABILITY</b>	Shrinkage After 70°C, 48 hours aging	0.64 mm
<b>PEEL ADHESION</b>	PSTC-1, 15 min, 21°C	0.45 kg/cm
<b>LINER RELEASE</b>	TLMI Release at 90°, 760 cm/min	11.81 g/cm

\* Recommended to test compatibility on raw & primed MDO prior to installation due to variation in substrate properties  
Standard Terms & Conditions Apply

## TERMS & CONDITIONS

*The following is made in lieu of all warranties expressed or implied:*

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

October 2019